

CONCRETE MIX



Lafarge Concrete Mix is a factory produced prescribed concrete mix; incorporating standardised binders and aggregates. This simple to use mixture, saves time and wastage for efficient application on smaller jobs.

GENERAL INFORMATION

Lafarge Concrete Mix is a premixed ready to use application composed of a blend of cement and aggregates.




FEATURES

- Simple to use, just add water
- Efficient and cost effective solution for small concrete jobs
- Contains 10mm aggregate and graded sand ensuring guaranteed mix properties
- 28 day strength 40N/mm²

APPLICATIONS

Ideal for small concrete jobs, including:

- Walkways, paths and steps
- Patios and slabs
- Backfill and infill
- Concrete shed bases
- General repair work and non-structural applications

<p>IDEAL FOR:</p>  <p>POST FIXING</p>  <p>CONCRETING</p>	<p>WEATHER RESISTANT PACKAGING</p> 
--	--

AVAILABILITY

Available in 20kg plastic bags.

STORAGE

This product must be stored in unopened bags clear of the ground. If stored correctly and used within 155 days of the packing date shown on this bag, the activity of the reducing agent* will be maintained and this product will contain, when mixed with water, no more than 0.0002% (2 ppm) soluble chromium (VI) of the total dry weight of cement. Use of this product after the end of the declared storage period (see above) may increase the risk of an allergic reaction.

MIXING GUIDANCE (BY VOLUME)

Factory produced prescribed concrete mix; incorporating standardized binders and aggregates.

Water Demand: Approx. 2.0-2.5 litres per bag.

Contents of the bag can be mechanically mixed with the required quantity of water for approx. 3-4 minutes in a free fall mixer or hand mixed by pouring the contents of the bag onto a clean, flat surface and slowly adding clean water and mixing continuously to achieve a workable concrete mix.

CONDITIONS OF USE

- Lafarge Concrete Mix should be applied within 30 minutes of adding water. Concrete should be fully compacted before finishing.
- Newly applied concrete should be covered with a polythene sheet or wet hessian (sacking) for protection for a minimum of 7 days.
- Clean all tools and equipment immediately after use and before the material has set.
- The final strength and finish of this product will depend on the user having the necessary skills and knowledge of the product and its application.

TECHNICAL SUPPORT

Should you require information for this or any other product within the Lafarge range, please contact our Customer Support team on 01285 646900 or visit our website at: www.lafargecement.co.uk

HEALTH AND SAFETY

Contact between cement powder and body fluids (e.g. eye fluids) may cause irritation, dermatitis or burns. Cement is classified as an irritant under the Chemicals (Hazard information and Packaging) Regulations. Please refer to the product safety data sheet for full information.

